



Penetrant Testing

Product information

MR[®] 68 C Penetrant red and fluorescent



MR[®] 68 C Penetrant red and fluorescent

for penetrant testing according to
EN ISO 3452-1:2013 and EN ISO 3452-6:2009

General appearance and composition:

- Water and solvent removable penetrant red and fluorescent
- Based on mineral oil, contains glycols
- Suitable for all metals
(suitability for plastics and ceramics needs testing prior to use)
- Without AZO-dye-stuff
- Suitable for very smooth surfaces
- Processing temperature **-10 to +50 °C**
- Aerosol overhead sprayable

Relevant approvals and specifications

- Sample testing acc. to EN ISO 3452-2:2006
- Sensitivity class 2 acc. to EN ISO 3452-2:2006
system IIAe
 - Remover: Water
 - Developer: MR[®] 70
- Sensitivity class 2 acc. to EN ISO 3452-2:2006 and EN ISO 3452-6:2009
system IIICe
 - Remover: MR[®] 79, MR[®] 85, MR[®] 88
 - Developer: MR[®] 70
- Sensitivity class 2 acc. to EN ISO 3452-2:2006
system IIIEe
 - Remover: Water, MR[®] 85
 - Developer: MR[®] 70
- Low content of halogens and sulphur according to EN ISO 3452-2:2006 and ASME Code V, Section V, Article 6
- Produits et Matériaux Utilisables en Centrales (PMUC)
- TLV 9017 01:2011-01

Application:

- Remove tinter, rust and other contaminations from surface in a suitable manner. A possible precleaner for removal of oils or fats is e.g. our remover MR[®] 79.
- Apply MR[®] 68 C Penetrant red and fluorescent to the part to be tested either by spraying, brushing, flooding or dipping. Allow to penetrate for at least 5 minutes.
- Remove excess penetrant from surface either using water or a clean lint-free cloth lightly moistened with an MR[®] Remover.
- Spray MR[®] Developer (e.g. MR[®] 70) from a distance of approx. 20 cm on the dry surface, achieving a thin, uniform layer. Surface defects will appear as red indications on a white background or fluorescent under UV-light. Please note: If the developer layer is too thick tiny discontinuities will not appear through the developer.



Penetrant Testing

Product information

MR[®] 68 C Penetrant red and fluorescent



Minimum shelf life:

- Will keep for a minimum of 4 years, stored at room temperature

Pack sizes:

- Aerosols, 500 ml (1 box contains 12 aerosols)
- 5 L, 30 L, 200 L
- Valve pen (Piccolo-Pen)